

# PROMOTOR ADESÃO II USO 2% A 4%

FR413 (REV. 01)

**TECHNICAL DATA SHEET** 

Auxiliary product indicated for use in flexo and gravure printing inks. Promotes immediate resin cure and high brightness maintenance, has high adhesion to the film Bioriented Polypropylene (BOPP), Polyethylene Terephthalate (PET) and increases milk resistance. Dosing up to 2% of the total ink volume is recommended.

## CODE: 019657-00

## **TYPICAL PROPERTIES**

Product type	Mixture
Aspect	Colorless liquid the pale yellow
Density	0,99 g/cm <sup>3</sup> (20 °C) (approximate value)
Viscosity	. ≈ 100 cP (approximate value)
Non volatile	. ≥ 60,0%

APPLICATION

Dosage	2% - 4% relative to the ink volume.								
	Values	above	this	limit	show	no	additional		
	efficacy	<i>'</i> .							

#### **APPLICATION INSTRUCTIONS**

Shake the contents with a mechanical stirrer. Make sure no pigment is trapped at the bottom of the container. Adjust the viscosity only after its perfect homogenization. During printing, the reservoir, the inkwell and the tin should remain closed. In stock keep cans tightly closed in a cool and well-ventilated place.

#### ANJO TINTAS





## SAFETY RECOMMENDATION

Store the product in sheltered, ventilated environments.

Flammable product, keep away from sparks, sources of ignition, do not smoke. Product when applied emanates vapors that should be avoided with the correct use of PPE, such as masks and respirators.

Avoid skin contact using gloves, goggles, proper clothing, protective creams etc. Keep away from contact with children and animals.

# STATUTORY REQUIREMENTS

<u>ANVISA</u> (Brazilian Health Regulatory Agency): Rules heavy metal levels for food packaging that may have contact with children;

<u>FDA</u> (Food and Drug Administration): Norm american regulating foods and drugs for toxicity;

<u>ABRE</u> (Associação Brasileira de Embalagens): Exclusion list to toxicity to inkd and solvente the print;

<u>EUPIA</u> (European Printing Ink Association): European exclusion list per toxicity in inks and solvent for printing.

## OBSERVATION

The instructions in this bulletin are based on our experience and technical knowledge, however, some factors are independent of our control as a manufacturer, such as:

substrate treatment, application, working conditions, and so forth. Due to substrate diversity and printing conditions, this sheet is sent for proposed information and is offered without warranty as it must be confirmed by industrial testing before products are used.

Use of thinner other than specified may affect product performance.





Anjo is constantly making improvements to its products and we reserve the right to change the contents of this technical bulletin without prior notice. Anjo is not responsible for improper use of the product.

Shelf life6 monthsPackingMetal bucket......16KgReview28/07/2020